

CLAIMS

What is claimed is:

- 5 1. An article made from a polyureaurethane aqueous dispersion.
2. The article of claim 1, wherein said article is selected from the group consisting of gloves, finger cots and condoms.
- 10 3. The article of claim 1, having a tensile strength of greater than 2030 psi.
4. The article of claim 1, having a puncture strength of at least 200 lb/in.
- 15 5. The article of claim 1, having a tear strength per thickness of material of at least 20 Newtons/mm.
6. The article of claim 1, having an improved resistance to solvent attack.
- 20 7. A process for producing the article of claim 1, comprising the steps:
 - a) dipping a mold into a coagulant solution and drying at an elevated temperature;
 - 25 b) dipping the coagulant solution-coated mold into an aqueous polyureaurethane dispersion and drying;
 - c) subjecting the coated mold to a salt leaching bath; and
 - d) drying the coated mold at elevated temperature before stripping the article off of said mold.